

FRIEDRICH KUEFFNER

PATENT AND TRADEMARK ATTORNEY

11/17/00
JCS57 U.S. PTO
09/17/00

11-20-00

342 MADISON AVENUE

SUITE 1921

NEW YORK, NEW YORK 10173

TELEPHONE: (212) 986-3114

TELECOPIER: (212) 986-3461

(212) 697-3004

EXPRESS MAIL No.: EL 599 503 441 US Deposited: November 17, 2000

I hereby certify that this correspondence is being deposited with the United States Postal Service Express mail under 37 CFR 1.10 on the date indicated above and is addressed to the Commissioner of Patents and Trademarks, Washington, DC 20231.

F. Kueffner

Friedrich Kueffner

ASSISTANT COMMISSIONER FOR PATENTS
Washington, DC 20231

Date: November 17, 2000

Docket No: HM-376

Sir:

Transmitted herewith for filing is the patent application of:

Inventor(s): Hans Streubel and Uwe Plociennik

FOR: METHOD FOR CONTINUOUS CASTING OF SLAB, IN PARTICULAR, THIN SLAB,
AND A DEVICE FOR PERFORMING THE METHOD

ENCLOSED ARE:

- (X) Specification (12 pages), Claims (4 pages/9 claims) & Abstract;
- (X) one (1) sheet of Drawing; (Figure 1)
- (X) Declaration and Power of Attorney; **UNSIGNED**
- () Assignment to SMS Demag AG
- () Certified copy of GermanPat.Appli.No: 199 56 577.5 filed Nov. 25, 1999
the priority of which is claimed under 35 USC 119;
- () Verified Statement to establish Small Entity Status (37 CFR 1.9 & 1.27);
- () Information Disclosure Statement, PTO-1449 and 3 references;

THE FILING FEE HAS BEEN CALCULATED AS SHOWN BELOW:

	Claims filed	Extra	SMALL ENTITY	or	LARGE ENTITY
Basic Fee			\$ 355.00		\$ 710.00
Total Claims	9	-20=	x \$ 9.=	x	\$ 18.=
Indep. Claims	2	- 3=	x \$ 40.=	x	\$ 80.=
() Multiple Dependent Claim Presented?			x \$135.=	x	\$270.=

Respectfully submitted

F. Kueffner

Friedrich Kueffner - Reg. No. 29,482

FK:ml

APPLICATION FOR UNITED STATES LETTERS PATENT

**METHOD FOR CONTINUOUS CASTING OF SLAB, IN
PARTICULAR, THIN SLAB, AND A DEVICE FOR PERFORMING
THE METHOD**

HM-376

BACKGROUND OF THE INVENTION

1. Field of the Invention

The invention relates to a method for continuous casting of bars, billets, slabs, in particular, thin slabs, in dimensional ranges of approximately 20 to 150 mm thickness and approximately 600 mm to 3,500 mm width, by means of an oscillating, water-cooled casting mold in cooperation with a submerged-entry nozzle with use of casting powder for forming casting cinder. The invention relates also to a device for performing the method.

2. Description of the Related Art

Methods and devices for continuous casting, in particular, of thin slab, are known and have been continuously improved during the course of the past developmental periods.

For example, it is known that, as a result of very different thermal conductivities of the different media interacting during continuous casting and the thus resulting resistances against thermal conduction and heat transmission, the formation of a strand skin of a continuous

cast strand presently being formed and especially its surface properties are variable within relatively wide limits. In particular, during thermal contact between the molten bath and the casting mold wall the thickness of the liquid cinder or slag of melted casting powder plays an important role because of its extremely minimal specific conductivity of approximately 1 W/K x m because it presents a significant resistance for the heat transmission between the melt and the casting mold plates. In contrast to the liquid slag, copper has an extremely high thermal conductivity of approximately 360 W/K x m.

As a result of the different individual resistance values of the thermal conductivity between copper, slag, and steel, different heat flux densities result within the casting mold plates which have a considerable effect on the solidification behavior of a strand to be cast.

The prior art published in connection with this problem includes, for example, documents DE 41 17 073 C2, DE 195 29 931 A1, and DE 198 10 672 A1.

In DE 41 17 073 C2 the temperature recordings of four water-cooled casting mold plates as integral values of each individual plate are measured and evaluated. No partial

measured values across the casting mold width are determined, and, in principle, the water quantity for cooling is not changed.

In DE 195 29 931 A1 a slab casting mold is described which is comprised of at least three independent cooling chamber segments which have separate connectors for an independent supply of casting mold cooling water in the area of the casting mold outlet. This arrangement is designed to detect asymmetries of the specific heat flux between the area of the submerged-entry nozzle and the remaining casting mold areas and to compensate them by conicality adjustment of the narrow sides of the casting mold and by cooling water regulation.

DE 198 10 672 A1 describes a method for measuring and controlling temperature and amount of the cooling water of a continuous casting mold per time unit flowing through water-coolable casting mold walls of copper plates, in particular, mold walls that are independent from one another. The invention resides in that the cooling water temperature of a casting mold wall is measured at least at two locations in the area of the outflow openings of a copper plate and the correlated water box and, based on the values measured across the width of the copper plate, a temperature profile

is produced and the temperature profiles obtained in time intervals are compared with one another. In this connection, the inflow temperature of the cooling water is measured, the difference of the inflow and outflow temperatures is determined, and, based on the cooling water amount per time unit, the partial integral heat transfer from a casting mold wall or a casting band area is determined, and partial inequalities are compensated by partial quantity corrections of the cooling water. The liquid-cooled casting mold for performing the method is designed such that in the water outflow area between a copper plate and the cooling water outflow opening of the water box, temperature sensors are arranged, in particular, at least at two locations per wide side plate, and their signal lines are connected to a computer, preferably provided with an online monitor.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide a method and a device for continuous casting of bars, billets, slabs, in particular, thin slabs, which are suitable to measure local temperatures and/or heat flux densities along the height of the casting mold walls and at several locations of its width extension and, based on this, to calculate the temperature load of the casting mold walls in contact with the melt, preferably in the meniscus area. By means of the measured values the operating parameters such as cooling water amount, casting speed, and casting powder are to be controlled such that at a preferred working temperature of the casting mold walls in the meniscus area an optimal surface formation of the slabs is made possible together with an availability of the casting mold as long as possible.

In accordance with the present invention, this is achieved with respect to the method in that the local temperatures and heat flux densities are measured in the meniscus area, which is critical for the surface quality of a slab, and that the working temperatures of the casting mold plates in the meniscus area are maintained within a predetermined temperature range (ΔT) by adjustment of the

operating parameters decisive therefor, such as the amount or throughput speed of the cooling water through the casting mold, casting speed, and casting powder to be used.

Accordingly, the temperature course along the height of the casting mold plates is determined and, based on this course, the maximum temperatures and thus the location of the meniscus area of the melt in the casting mold are determined. When the optimal heat flux density is known, it is possible to improve the surface quality of the products produced in the continuous casting process, especially for thin slabs.

One embodiment of the method suggests that the working temperatures of the casting mold plates are measured by thermoelements arranged at a defined spacing and within a height level (Y_i $i = 1$ to n) above and below the bath level (M), respectively.

In a further embodiment of the method according to the invention, it is proposed that the thermoelements are arranged at different depths (X_1, X_2) of the wall of the casting mold and that, based on the temperature difference of at least two thermoelements positioned approximately at the same height area (Y_i , e.g., y_1, y_2), the corresponding

local heat flux density is calculated.

The thus determined results in regard to the course of the heat flux density make it possible to correct online deviations from a predetermined course with the accordingly provided operational parameters.

Moreover, an embodiment of the method according to the invention proposes that, by determining the temperature course or heat flux course along the height of a wall of the casting mold, the maximum temperature course of the wall surface in contact with the melt is determined by means of approximation functions. According to a further development of the method it is suggested that, when detecting a heat flux density change at the height (y) of the casting mold as a result of two-dimensional heat distribution in the bath level area (M), the position of the bath level (M) is determined online by employing an assumed heat flux density course at one surface of the casting mold and the known heat flux density in the depth (x) of a casting mold wall.

Finally, a further embodiment of the method according to the invention suggests that the best suited casting mold thermal load for an optimal slab surface formation is controlled by adjusting the cooling water quantity and/or

the casting speed and/or the casting powder, when the optimal heat flux density or the maximum surface temperature of the casting mold is known.

A device according to the invention, provided for performing the method according to the invention of measuring local temperatures and/or heat flux densities on a water-cooled casting mold during continuous casting of bars, billets, slabs, in particular, thin slabs, is defined in that thermoelements are embedded in a paired arrangement in the wide lateral sidewalls of the casting mold in an area above and below the bath level and with approximately identical spacing from its contact surface with the melted liquid metal. The thermoelements are connected via signal lines with a computer unit which, based on the measured temperature or heat flux density, calculates the surface temperature of the casting mold in the meniscus area and, for controlling a preferred working temperature of the casting mold wall within a predetermined temperature range (ΔT), adjusts the operating parameters cooling water quantity, casting speed, as well as casting powder.

BRIEF DESCRIPTION OF THE DRAWING

In the drawing:

Fig. 1 shows a temperature profile or a heat flux course along the height (y) of a casting mold wall as well as in at least two spaced areas (x_1 , x_2) of the casting mold wall spaced from the melt bath (M).

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The temperature profile or heat flux course along the height (y) of a continuous casting wall as well as in at least two spaced areas (x_1, x_2) of the casting mold wall spaced from the melt bath (M) is illustrated in Fig. 1. The course of the curve shown in solid line ($y_1, y_3, y_5, y_7, y_9, y_{11}$) shows a definite temperature maximum (T_{\max}) in the area of a predetermined temperature range (ΔT). The measuring points ($y_2, y_4, y_6, y_8, y_{10}, y_{12}$), positioned farther into the interior of the casting mold wall, show a similar curve with temperature maximum (T_{\max}) in the meniscus area (M). Based on the measured temperature profiles the temperature profile of the casting mold surface is calculated.

The temperature curves can be recorded online and shown on a display by means of an electronic measuring device. They can be used to keep the temperature constant in the predetermined temperature window (ΔT) by automatic control of the decisive operating parameters in order to achieve an optimal surface formation, for example, in the case of a thin slab.

While specific embodiments of the invention have been shown and described in detail to illustrate the inventive

principles, it will be understood that the invention may be embodied otherwise without departing from such principles.

What is claimed is:

1. A method for continuous casting bars, billet, and slabs from a melt in dimensional ranges of approximately 20 to 150 mm thickness and approximately 600 to 3500 mm width by means of an oscillating, water-cooled casting mold in cooperation with a submerged-entry nozzle, employing casting powder for formation of casting slag, the method comprising the steps of:

measuring local temperatures and local heat flux densities of a casting mold in a meniscus area of the melt critical for the surface quality of a slab; and

maintaining working temperatures of the casting mold plates in the meniscus area by adjusting the operating parameters important for the working temperature within a predetermined temperature range (ΔT).

2. The method according to claim 1, wherein the operating parameters are selected from the group consisting of the quantity of the cooling water, the throughput speed of the cooling water through the casting mold, the casting speed, and the casting powder to be used.

3. The method according to claim 1, wherein the slab is a thin slab.

4. The method according to claim 1, further comprising the step of arranging thermoelements in the casting mold plates at a defined spacing from one another and within a height range above and below the bath level, respectively, for determining the working temperatures of the casting mold plates.

5. The method according to claim 4, wherein the thermoelements are arranged at different depths in the casting mold wall and wherein, based on a temperature difference of at least two of the thermoelements positioned substantially at the same height, the corresponding local heat flux density is calculated.

6. The method according to claim 1, further comprising the step of calculating a maximum temperature course of the wall surface in contact with the melt by means of approximation functions, based on a determination of the course of the local temperatures or the heat flux along a height of the casting mold wall.

7. The method according to claim 6, wherein, when a change of the heat flux density is determined along the height of the casting mold wall as a result of two-dimensional heat transfer in the area of the bath level (M),

the position of the bath level (M) is determined based on an assumed heat density course in a casting mold surface and the known heat flux density in the depth (x) of a casting mold wall.

8. The method according to claim 1, further comprising the step of controlling, when knowing the optimal current density or the maximum surface temperature, the best suited casting mold load for an optimal slab surface formation by adjusting at least one of the operating parameters selected from the group consisting of cooling water quantity and casting speed and casting powder.

9. A device for determining at least one of local temperatures and heat flux densities in a water-cooled continuous casting mold during continuous casting of bars, billets, and slabs, for performing the method according to claim 1, the device comprising:

thermoelements arranged in a paired arrangement in wide lateral sidewalls of the casting mold in an area above and below a bath level and with approximately identical spacing from the contact surface of the casting mold wall with the melted liquid metal;

a computer;

the thermoelements connected via signal lines to

the computer;

the computer being configured to calculate, based on measured temperatures or heat flux density, a surface temperature of the casting mold wall in the meniscus area;

the computer being configured to control a preferred working temperature of the casting mold wall within a predetermined temperature range (ΔT) by adjusting the operating parameters selected from the group consisting of cooling water quantity, casting speed, and casting powder.

ABSTRACT OF THE DISCLOSURE

In a method for continuous casting bars, billets, and slabs from a melt in dimensional ranges of approximately 20 to 150 mm thickness and approximately 600 to 3500 mm width by means of an oscillating, water-cooled casting mold in cooperation with a submerged-entry nozzle and by employing casting powder for formation of casting slag, local temperatures and local heat flux densities of a casting mold wall in a meniscus area of the melt critical for the surface quality of a slab are measured. The working temperature of the casting mold wall in the meniscus area is maintained by adjusting the operating parameters important for the working temperature within a predetermined temperature range (ΔT).

Declaration and Power of Attorney for Patent Application
Erklärung für Patentanmeldungen mit Vollmacht
German Language Declaration

Als nachstehend benannter Erfinder erkläre ich hiermit an Eides Statt:

daß mein Wohnsitz, meine Postanschrift, und meine Staatsangehörigkeit den im Nachstehenden nach meinem Namen aufgeführten Angaben entsprechen,

daß ich, nach bestem Wissen der ursprüngliche, erste und alleinige Erfinder (falls nachstehend nur ein Name angegeben ist) oder ein ursprünglicher, erster und Miterfinder (falls nachstehend mehrere Namen aufgeführt sind) des Gegenstandes bin, für den dieser Antrag gestellt wird and für den ein Patent beantragt wird für die Erfindung mit dem Titel:

**VERFAHREN ZUM STRANGGIEßEN VON BRAMMEN,
INSBESONDERE VON DÜNNBRAMMEN, SOWIE EINE
VORRICHTUNG ZU DESSEN DURCHFÜHRUNG**

deren Beschreibung
(Zutreffendes ankreuzen)

☒ hier beigefügt ist.

☐ am _____ unter der
Anmeldungsseriennummer _____
eingereicht wurde und am _____
abgeändert
wurde (falls tatsächlich abgeändert).

Ich bestätige hiermit, daß ich den Inhalt der obigen Patentanmeldung einschliesslich der Ansprüche durchgesehen und verstanden habe, die eventuell auch einen Zusatzantrag, wie oben erwähnt, abgeändert wurde.

Ich erkenne meine Pflicht zur Offenbarung irgendwelcher Informationen, die für die Patentierbarkeit in Einklang mit Absatz 37, Bundesgesetzbuch, Paragraph 1.56(a) von Wichtigkeit sind, an.

Ich beanspruche hiermit ausländische Prioritätsvorteile gemäss Abschnitt 35 der Zivilprozessordnung der Vereinigten Staaten, Paragraph 119 aller unten angegebenen Auslandsanmeldungen für ein Patent oder eine Erfindersurkunde, und habe auch alle Auslandsanmeldungen für ein Patent oder ein Erfindersurkunde nachstehend gekennzeichnet, die ein Anmeldedatum haben, das vor dem Anmeldedatum der Anmeldung liegt, für die Priorität beansprucht wird.

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**METHOD FOR CONTINUOUS CASTING OF SLAB,
IN PARTICULAR, THIN SLAB, AND A DEVICE
FOR PERFORMING THE METHOD**

the specification of which (check one)

☒ is attached hereto

☐ was filed on Application Serial No. _____
and was amended on _____
(if applicable)

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed.

Erklärung mit Vollmacht (auf Deutsch)

Declaration and Power of Attorney (in English)

<u>199 56 577.5</u>	<u>Germany/Deutschland</u>	<u>Nov. 25, 1999/25. November 1999</u>	<u>X</u>	
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No
(Nummer)	(Land)	(Tag/Monat/Jahr eingereicht)	Ja	Nein
<hr/>				
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No
(Nummer)	(Land)	(Tag/Monat/Jahr eingereicht)	Ja	Nein
<hr/>				
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No
(Nummer)	(Land)	(Tag/Monat/Jahr eingereicht)	Ja	Nein

Ich beanspruche hiermit gemäss Absatz 35 der Zivilprozessordnung der Vereinigten Staaten, Paragraph 120, den Vorzug aller unten aufgeführten Anmeldungen und falls der Gegenstand aus jedem Anspruch dieser Anmeldung nicht in einer früheren amerikanischen Patentanmeldung laut dem ersten Paragraphen des Absatzes 35 der Zivilprozessordnung der Vereinigten Staaten, Paragraph 112, offenbart ist, erkenne ich gemäss Absatz 37, Bundesgesetzbuch, Paragraph 1.56(a) meine Pflicht zur Offenbarung von Informationen an, die zwischen dem Anmeldedatum der früheren Anmeldung und dem nationalen oder internationalen Anmeldedatum dieser Anmeldung bekannt sind.

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing date of the prior application and the national or international filing date of this application.

<u>(Application Serial No.)</u>	<u>(Filing Date)</u>	<u>(Status/ patentiert</u>	<u>(Status/ patented,</u>
<u>(Anmeldeseriennummer)</u>	<u>(Anmeldedatum)</u>	<u>anhangig, aufgegeben)</u>	<u>pending, abandoned)</u>
<hr/>			
<u>(Application Serial No.)</u>	<u>(Filing Date)</u>	<u>(Status/ patentiert</u>	<u>(Status/ patented,</u>
<u>(Anmeldeseriennummer)</u>	<u>(Anmeldedatum)</u>	<u>anhangig, aufgegeben)</u>	<u>pending, abandoned)</u>

Ich erkläre hiermit, daß alle von mir in der vorliegenden Erklärung gemachten Angaben nach meinem besten Wissen und Gewissen der vollen Wahrheit entsprechen, und daß ich diese eidesstattliche Erklärung in Kenntnis dessen abgebe, daß wissentlich und vorsätzlich falsche Angaben gemäss Paragraph 1001, Absatz 18 der Zivilprozessordnung der Vereinigten Staaten von Amerika mit Geldstrafe belegt und/oder Gefängnis bestraft werden können, und daß derartig wissentlich und vorsätzlich falsche Angaben die Gültigkeit der vorliegenden Patentanmeldung oder eines darauf erteilten Patentes gefährden können.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under §1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Erklärung mit Vollmacht (auf Deutsch)

Declaration and Power of Attorney (in English)

VERTRETUNGSVOLLMACHT: Als benannter Erfinder beauftrage ich hiermit den nachstehend benannten Patentanwalt (oder die nachstehend benannten Patentanwälte) und/oder Patent-Agenten mit der Verfolgung der vorliegenden Patentanmeldung sowie mit der Abwicklung aller damit verbundenen Geschäft vor dem Patent-und Warenzeichenamt:

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

FRIEDRICH KUEFFNER, Reg. No. 29,482

FRIEDRICH KUEFFNER, Reg. No. 29,482

Telefongespräche bitte richten an:
(Name und Telefonnummer)

Direct telephone calls to:
(Name and telephone number)

Friedrich Kueffner
(212) 986-3114

Friedrich Kueffner
(212) 986-3114

Postanschrift:

Send Correspondence to:

Friedrich Kueffner
342 Madison Avenue, Suite 1921
New York, NY 10173

Friedrich Kueffner
342 Madison Avenue, Suite 1921
New York, NY 10173

Voller Name des einzigen oder ursprünglichen Erfinders:

Hans Streubel

Full name of first or sole inventor:

Hans Streubel

Unterschrift des Erfinders

Datum

Inventor's Signature

Date

Erkrath, Deutschland
Wohnsitz

Erkrath, Germany
Residence

Deutsch
Staatsangehörigkeit

German
Citizenship

Schlüterstraße 30

Schlüterstrasse 30

40699 Erkrath, Deutschland
Postanschrift

40699 Erkrath, Germany
Post Office Address

Erklärung mit Vollmacht (auf Deutsch)

Declaration and Power of Attorney (in English)

Voller Name des zweiten Miterfinders:		Full name of second joint inventor:	
Uwe Plociennik		Uwe Plociennik	
Unterschrift des Erfinders	Datum	Inventor's Signature	Date
<u>Ratingen, Deutschland</u>		<u>Ratingen, Germany</u>	
Wohnsitz		Residence	
<u>Deutsch</u>		<u>German</u>	
Staatsangehörigkeit		Citizenship	
<u>Noldenkothen 21</u>		<u>Noldenkothen 21</u>	
<u>40882 Ratingen, Deutschland</u>		<u>40882 Ratingen, Germany</u>	
Postanschrift		Post Office Address	